

PP P310

Features	Applications
➤ ➤	➤

Properties	Test Method	Test Condition	Unit	
Physical				
Melt Index	ISO 1133	230 ,2.16kg	g/10min	16
Specific Gravity	ISO 1183	23	g/cm ³	0.975
Mechanical				
Tensile Strength	ISO 527	50mm/min	MPa	33
Flexural Modulus	ISO 178	2mm/min	MPa	2200
Notched Izod Impact (23)	ISO 180	2.75J	KJ/m ²	3.8
Thermal				
Heat Distortion Temp.	ISO 75	0.45MPa		120