

Properties	Test Method	Test Condition	Unit	Typical Values
Physical				
Filler Content	ISO 3451	625 5	%	31
Mechanical				
Tensile Strength@Yield	ISO 527	10mm/min	MPa	90
Flexural Strength	ISO 178	2mm/min	MPa	120
Flexural Modulus	ISO 178	2mm/min	MPa	6000
Notched Izod Impact Strength	ISO 180	23	Kj/m ²	10
Izod Impact Strength	ISO 180	23	Kj/m ²	35
Thermal				
Heat Deflection Temperature	ISO 75	1.80MPa		150