

◇	◇
◇	◇

Properties	Test Method	Test Condition	Unit	Typical Values
Physical				
Specific Gravity		23	g/cm ³	1.52
Ash		800	%	40
Mechanical				
Tensile Strength		10mm/min	MPa	185
Nominal strain at break		10mm/min	%	2
Flexural Strength		2mm/min	MPa	266
Flexural Modulus		2mm/min	GPa	16
Notched Charpy Impact Strength		23	KJ/m ²	10
Thermal				
Heat deflection temperature		1.80MPa		210

✓

✓