


Dawnflex TPU DN-3198

FEATURES

A kind of polyether type thermoplastic polyurethane (TPU) materials, with good physical properties, high elasticity, good processing fluidity and aging resistance excellent hydrolysis resistance and low temperature flexibility and dimensional stability is mainly used for extrusion and calendaring products. It is non-toxic and environmentally friendly material, and completely recyclable.

General information				
Application		Extrusion products		
RoHS	RoHS compliance	Complied		
Color		Colorless		
Appearance		Particle		
Processing method		Extrusion Calendaring		
Revision period		2019-06-25		
Performace parameters		Typical value	Unit	Method
Density		1.21	g/cm³	ASTM D792
Shore Hardness		97	A	ASTM D2240
Tensile strength		35.02	MPa	ASTM D412
100%	100% proof strength	16.93	MPa	ASTM D412
300%	300% proof strength	25.16	MPa	ASTM D412
Elongation at break		501	%	ASTM D412
Tear strength		156	KN/m	ASTM D624
Moisture content		0.03	%	ASTM D4019
Processing conditions				
0.05%				
Drying Instructions: Need drying the granules before make molding, excessive moisture will lead materials bad extrusion surface, mechanical performance reduction and bad surface appearance. Moisture content request below 0.05%,suggesting drying as follow process:				
Drying conditions	Drying temperature/		Drying time/h	
	95-100		2-3	
100		100		
If drying temperature over than 100 , it might cause materials blocking in barrel zone; if use moisture analysis meter, the temperature setting should be on 100 .				
				
/	/	/	/	/
175-185	185-200	190-205	195-205	190-200

Extra information

-
1.
The above properties are typical performance which is not regarding as technical index or agreement.
2.
Above instructions for reference only, different equipment might have difference parameters, please adjust accordingly with different mold and product shape.

SHANDONG DAWN POLYMER CO.,LTD
:
: 265703
Address: Zhenxing Road, Longgang Economic Zone, Longkou, Shandong, China. 265703
() 0086-535-8868588;()0086-535-8833988
Tel:(Foreign Trade) 0086-535-8868588;(Domestic Trade)0086-535-8833988