

Dawnflex TPU DN-E195

21092806

FEATURES

A kind of thermoplastic polyurethane (TPU) materials, with good physical properties, high transparency, excellent elasticity, good processing fluidity and fast forming speed performances, is mainly used for injection products extrusion product and calendered products. It is non-toxic and environmentally friendly material, and completely recyclable.

General information				
Application		Injection products extrusion products Calendered products		
RoHS	RoHS compliance	Complied		
Color		Colorless, transparent		
Appearance		Particle		
Processing method		Injection Extrusion Calendered		
Revision period		2021-09-30		
Performace parameters		Typical value	Unit	Method
Density		1.243	g/cm³	ASTM D792
Shore Hardness		95	A	ASTM D2240
Tensile strength		21.8	MPa	ASTM D412
100%	100% proof strength	11.25	MPa	ASTM D412
300%	300% proof strength	9.62	MPa	ASTM D412
Elongation at break		576.94	%	ASTM D412
Tear strength		127	KN/m	ASTM D624
Moisture content		0.05	%	ASTM D4019
Processing conditions				
0.05%				
Drying Instructions: Need drying the granules before make molding, excessive moisture will lead materials bad extrusion surface, mechanical performance reduction and bad surface appearance. Moisture content request below 0.05%,suggesting drying as follow process:				
Drying conditions		Drying temperature/		Drying time/h
		100		2-4
100				



/	/	/	/	/	/	/
-	-	195-210	210-220	215-225	225-235	35-50

Extra information

1.
The above properties are typical performance which is not regarding as technical index or agreement.
2.
Above instructions for reference only, different equipment might have difference parameters, please adjust accordingly with different mold and product shape.

SHANDONG DAWN POLYMER CO.,LTD
：. 265703
Address: Zhenxing Road, Longgang Economic Zone, Longkou, Shandong, China. 265703
() 0086-535-8868588;()0086-535-8833988
Tel:(Foreign Trade) 0086-535-8868588;(Domestic Trade)0086-535-8833988