

Dawnflex TPU DN-1090-T1

地			
	25kg/		
	1.20	g/cm ³	ASTM D792
	93 1	A	ASTM D2240
	40	MPa	ASTM D412
100%	10	MPa	ASTM D412
300%	15	MPa	ASTM D412
	550	%	ASTM D412
	140	KN/m	ASTM D624
100	0.05%		公
100			
	/	/h	
	90-100	2-4	
	210-220		195-205
	205-215		190-200
	205-215		190-200
	200-210		185-195
SDS			
1.			
2.			
:	. 265703		
() 0086-535-8868588;		()0086-535-8833988

Dawnflex TPU DN-1090-T1

General information			
Material Properties	Good formability, high transparency, low precipitation risk, easy to post-processing		
Application Market	Electronic injection molding, pneumatic tubing, modification, shoe materials		
Appearance Shape	Transparent particles		
Packing Specifications	25 kg/bag		
Processing Method	Injection Extrusion		
Physical property parameters	Typical value	Unit	Method
Density	1.20	g/cm ³	ASTM D792
Shore Hardness	93 1	A	ASTM D2240
Tensile Strength	40	MPa	ASTM D412
100% Modulus	10	MPa	ASTM D412
300% Modulus	15	MPa	ASTM D412
Elongation at Break	550	%	ASTM D412
Tear Strength	140	KN/m	ASTM D624
Processing suggestions			
Processing conditions Drying Instructions: Need drying the granules before make molding, excessive moisture will lead materials bad extrusion surface, mechanical performance reduction and bad surface appearance. Moisture content request below 0.05%, suggesting drying as follow process:			
Drying conditions	Drying temperature/		Drying time/h
	90-100		2-4
Processing temperature			
Injection	Set Value	Extrusion	Set Value
Nozzle ()	210-220	Nozzle ()	195-205
Front Barrel ()	205-215	Front Barrel ()	190-200
Middle Barrel ()	205-215	Middle Barrel ()	190-200
Rear Barrel ()	200-210	Rear Barrel ()	185-195
Healthy Safety Environmental: Take SDS for reference			
Extra information 1.The above properties are typical performance which is not regarding as technical index or agreement. 2.Above instructions for reference only, different equipment might have difference parameters, please adjust accordingly with different mold and product shape.			
SHANDONG DAWN POLYMER Co., Ltd. Address: Zhenxing Road, Longgang Economic Zone, Longkou, Shandong, China. 265703 Tel:(Foreign Trade) 0086-535-8868588;(Domestic Trade)0086-535-8833988			