



'N 7

TPV

TPV

Features:

A soft, black thermoplastic vulcanizate (TPV) in the thermoplastic elastomer (TPE) family. This material combines good physical properties, chemical resistance and elasticity, designed for extrusion and injection applications. This grade of TPV can be processed on conventional thermoplastics equipment for extrusion, injection molding. It is polyolefin based and completely recyclable.

RoHS	RoHS		
	2020-8-18		
	0.9: 7	g/cm ³	ASTM D792
(Shore A,15 sec,23)	6: .0	A	ASTM D2240
100% - 23	2.30	Mpa	ASTM D412
- 23	9.20	Mpa	ASTM D412
- 23	550	%	ASTM D412
- 23 Die C	30.5	KN/m	ASTM D624
23 , 70hr, 1 B	35	%	ASTM D395
70 , 22hr, 1 B	40	%	
	-60		ASTM D746
	25	mm/min	GB 8410
(100 , 168hr)	-4.0	%	ASTM D573
(100 , 168hr)	-8.0	%	
(100 , 168hr)	+1	A	
200PPHM 40 *72		—	ASTM D7762

0.01%


Drying Instructions: Need drying the granules before make molding, excessive moisture will lead materials bad extrusion surface, mechanical performance reduction and bad surface appearance. Moisture content request below 0.01%,suggesting drying as follow process:

Drying conditions	Drying temperature/	Drying time/h
first choice	80 90	2 3
other choice	100	1

110

105

If drying temperature over than 110 ,it might cause materials blocking in barrel zone; if use moisture analysis meter, the temperature set should be 105 .



R							
40-150	160-170	180-185	190-210	190-215	180-205	170-185	50-70

1.Dawnprene TPV PVC

Dawnprene TPV is incompatible with PVC materials, hence must clean the equipment before using.

2. 120 × 100 × 2 , .

Above testing data is tested by mould sample block, cutting by the sheet size is 120 × 100 × 2 .

3. 25%

Compression Set 25%

4.

The properties is typical performance, is not regarding as technical index or agreement.

5.

Any reprocessing must follow the above instructions, and ensure that no impurity would be introduced.

6.

Above instructions for reference only, different equipment might have difference parameters, please adjust accordingly to different mold and product shape.

SHANDONG DAWN POLYMER CO.,LTD

: . 265703

Address: Zhenxing Road, Longgang Economic Zone, Longkou, Shandong, China. 265703

() 0086-535-8868588;()0086-535-8833988

Tel:(Foreign Trade) 0086-535-8868588;(Domestic Trade)0086-535-8833988